

Belzona 5841

FN10103



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

Belzona® 5841 is tolerant of surface preparation. It is, however, recommended that the best possible surface preparation is carried out. As a minimum, substrate surface must always be clean and firm.

RECOMMENDED PROCEDURE

- i) Brush away loose contamination and degrease with a rag soaked in **Belzona® 9111** (cleaner/degreaser) or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK). Use a flame to sweat out oil from deeply impregnated surfaces.
- ii) Blast clean the metal surface to achieve the following minimum standard of cleanliness:
ISO 8501-1 Sa 2 thorough blast cleaning
SSPC SP-6 commercial blast cleaning
Swedish Standard Sa 2 SIS 05 5900.
- iii) UHP Hydroblasting (2000 - 2500 bar) to remove previous coatings and expose original profile.
- iv) Power tool clean (MBX Bristle Blaster, grinders etc.) in accordance with SSPC-SP3 to remove contamination and achieve a minimum SSPC-SP11 bare metal power tool cleaned surface (ISO 8501-1 grade St 3).

WHERE BELZONA® 5841 SHOULD NOT ADHERE

Brush on a thin layer of **Belzona® 9411** (Release Agent) and allow to dry for 15-20 minutes before proceeding to step 2.

2. COMBINING THE REACTIVE COMPONENTS

Transfer the entire contents of the Solidifier container into the Base container. Mix thoroughly together to achieve a uniform material free of any streakiness.

NOTES:

1. MIXING AT LOW TEMPERATURES

To ease mixing when the material temperature is below 50°F (10°C), warm the Base and Solidifier modules until the contents attain a temperature of 68-77°F (20-25°C).

2. APPLICATION TEMPERATURES

Belzona® 5841 is designed to be applied to warm surfaces between 86°F and 176°F (30°C and 80°C).

3. WORKING LIFE

From the commencement of mixing, **Belzona® 5841** must be used within the times shown below.

Temperature	50°F (10°C)	77°F (20°C)	86°F (30°C)
Use all material within	2 hours	1 hour	30 min

4. MIXING SMALL QUANTITIES

For mixing small quantities of **Belzona® 5841** use:
4 parts Base to 1 parts Solidifier by volume
8.5 parts Base to 1 parts Solidifier by weight

3. APPLYING BELZONA® 5841

FOR BEST RESULTS

Do not apply when:

- (i) Rain, snow, fog or mist is present.
- (ii) There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- (iii) The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

a) FIRST COAT

Apply the **Belzona® 5841** directly on to the hot prepared surface with a short bristled brush. The substrate temperature must be between 86°F and 176°F (30°C and 80°C) for acceptable cure.

The applied coating thickness will depend on the substrate temperature, see below. Use a wet film thickness gauge to regularly check that the correct film thickness is being achieved.

Substrate temperature	Wet Film Thickness/coat	Theoretical coverage rate/coat
86°F (30°C)	8 mils (200 microns)	27 sq.ft./kg (2.5 m²/kg)
122°F (50°C)	6 mils (150 microns)	35.6 sq.ft./kg (3.31 m²/kg)
176°F (80°C)	4 mils (100 microns)	53.6 sq.ft./kg (4.98 m²/kg)

b) SECOND COAT

As soon as possible after application of the first coat, apply a further coat of **Belzona® 5841** as in (a) above. The minimum overcoating time will be dependent on the temperature of the substrate, as indicated in the table below:

Substrate temperature	Touch dry time
86°F (30°C)	2½ hours
122°F (50°C)	1 hour
176°F (80°C)	20 min

The maximum recommended overcoating time is 24 hours, irrespective of cure temperature.

c) THEORETICAL COVERAGE RATES

Coverage rate is also dependent on substrate temperature. For a two coat system:

Substrate temperature	Theoretical coverage rate
86°F (30°C)	13.5 sq.ft. (1.25 m ²)/kg
122°F (50°C)	17.8 sq.ft. (1.66 m ²)/kg
176°F (80°C)	26.8 sq.ft. (2.49 m ²)/kg

d) PRACTICAL COVERAGE RATES

In practice many factors influence the exact coverage rate achieved. On rough surfaces such as pitted steel the coverage rate achieved may be reduced by up to 20%.

NOTE:**CLEANING**

Brushes or any other application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Belzona® 5841 will continue to cure whilst the substrate remains hot. Cure times will depend on the substrate temperature, as indicated in the table below:

Substrate temperature	Touch dry/Light loading	Full cure
86°F (30°C)	2½ hours	24 hours
122°F (50°C)	1 hour	16 hours
176°F (80°C)	20 min.	8 hours

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2017 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

